



RJR POLYMERS, INC.

### Flammability Ratings of RJR Plastics and Epoxies

Material Tested	Test Method/Procedure	Result/Rating
Plastic Molding Compound Ingredients	UL94	V0 with Burn Length of 1/32 inch
RJR Epoxy	UL94 not applicable to thin film products	*See below
Plastic Molding Compound Ingredients & RJR Epoxy	D2863 (min % of oxygen required to marginally support combustion)	>40%

\*No significant decomposition or combustion occurs below ~400°C, and the combustion products are typical of natural or synthetic organic compounds. Similar materials like epoxy molding compounds and glass filled PC boards also have V0 ratings. There are no halogen or asbestos compounds present in any of our materials.

*This data is provided for guideline purposes only. No warranty is made on the actual use. Customers should perform their own tests.*